

## FEATURES

### Advantages:

- Fast cure at normal temperatures
- Rapid Dry to Recoat
- Ready to use as soon as components are mixed - no induction time required
- Good solvent resistance
- Resists solvent entrapment
- Good gloss hold-out
- Ideal tie-coat over inorganic zinc's
- Safe - contains no heavy metals or silica
- Excellent adhesion to almost any surface
- Versatile - can be used as the primer under all E~Line®, Altra~Shield®, Altra~Build® systems and Chem-Bar™ 900

### Limitations of Use:

- Do not top-coat with alkyd coatings without testing
- Has a definite end of pot life should not be kept overnight
- Cure is slowed down at temperatures below 4 °C

## RECOMMENDED USES

Altra-Prime® 514 is a high performance multi- purpose, two component epoxy primer zinc phosphate designed for use in both interior and exterior exposure over a variety of suitably prepared surfaces including:

- Steel
- Galvanised Metal
- Fibreglass

Altra-Prime® 514 may also be used over suitably prepared, aged epoxy and urethane paint systems.

## SPECIFICATION DATA

<b>Coating Type:</b>	Polyamide Epoxy
<b>Colour:</b>	Pipeline Grey N43
<b>Packaging:</b>	20 litre (Made to order)
<b>Mix Ratio:</b>	9:1 by volume
<b>Gloss:</b>	Flat
<b>Flash Point:</b>	27 °C Setaflash
<b>Thinner:</b>	½ Thinner
<b>Pot Life:</b>	12 hours at 25 °C
<b>Induction Time:</b>	Summer – not required Winter – 15 minutes
<b>Storage:</b>	Store under cool dry conditions

<b>Density:</b>	1.59 kg per litre
<b>VOC:</b>	339 g per litre
<b>Temperature Resistance:</b>	120 °C dry
<b>Volume solids (mixed):</b>	67 %
<b>Theoretical Coverage Rate:</b>	8.9 sq. metres per litre at 75 microns dry
<b>Recommended Film Thickness Per Coat:</b>	110-185 microns wet to obtain 75-125 microns dry
<b>Application:</b>	Spray, Brush or Roller

### Dry Times (75µm DFT / 50% RH):

Recoat – minimum:	5 °C	15 °C	25°C	30°C
Self	9 hrs	3 hrs	1.5 hrs	1 hr
Epoxy	9 hrs	3 hrs	1.5 hrs	1 hr
Urethane	12 hrs	4 hrs	2 hrs	2 hrs
Recoat – maximum:	5 °C	15 °C	25°C	30°C
Self	1440 hrs	1440 hrs	1440 hrs	1440 hrs
Epoxy	1440 hrs	1440 hrs	1440 hrs	1440 hrs
Urethane	96 hrs	96 hrs	96 hrs	72 hrs

## SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Oil or grease should be removed in accordance with AS1627.1 solvent cleaning. Surface defects revealed by the preparation process, should be ground, filled, or treated in the appropriate manner. Clean to remove all grit dust and debris and ensure the surface is dry.

### Steel Surfaces:

Abrasive blast to AS1627.4 Class 3 for immersion service and for non-immersion to AS1627.4 Class 2 ½ to achieve a uniform blast profile between 38 to 63 microns and be of a jagged nature as opposed to a peen pattern. A lesser degree of cleaning will reduce the service life of the coating. Apply primer coat to the cleaned surface to prevent re-rusting or contamination.

### Galvanised Steel and Electrodepositing Zinc Surfaces:

All traces of dichromate passivation must be removed. Sweep abrasive blast with non-metallic media or thoroughly sand with synthetic scouring pad to provide a uniform roughened finish.

### GRP and Wooden Surfaces:

Thoroughly sand with non-stearate paper with 80-120 grit

### Concrete surfaces:

Concrete must cure for at least 28 days and not be greater than 10 pH. Acid etch with dilute hydrochloric acid solution (1 part concentrated acid to 10 parts water) to produce a uniformly roughened surface profile, followed by washing off with copious amounts of clean fresh water until the cleaning water is neutral to litmus paper. DO NOT allow etch solution to dry on the surface. Check for excessive moisture using the ASTM D-4263 "Plastic Sheet Method" test. Grinding or sweep blasted to remove all laitence may also be carried out.

### Previously Painted Surfaces:

Clean with Altex P40 Cleaner. Remove all unsound coatings. Prepare all corroded and damaged paint areas in accordance with the preparation required for the applicable primer. Feather back edges to a sound clean existing coating. Matt all existing coating to provide a fine matt finish. Clean to remove all grit dust and debris and ensure the surface is dry.

Apply a test patch to confirm compatibility with existing coating system. If lifting occurs remove to bare substrate.

## DIRECTIONS FOR USE

### Mixing:

Altra-Prime<sup>®</sup> 514 is a two component product supplied in 20 litre kits which contain the correct ratio of ingredients. Power mix the base portion first to obtain a smooth homogeneous condition. After mixing the base portion, slowly add the converter whilst continuing to agitate at slow speed. After addition of the converter is complete, continue to mix slowly until homogeneous.

Higher temperatures will reduce the working life of the coating; lower temperatures will increase it.

### Thinning:

Thinning maybe required to assist application. Any solvent addition should be made after the two components are thoroughly mixed. Excessive thinning can cause low film thickness and coating defects.

### Clean-up:

Use ½ thinner

### Application:

Application by airless or conventional air spray equipment is the preferred method of application. Altra-Prime<sup>®</sup> 514 may also be applied to small areas by brush and roller.

Suggested conventional spray equipment is:

Air Spray:	Graco - Delta Air spray gun, 2.8mm (0.110") or 2.2mm (0.086") set up De Vilbiss - JGA gun, E or D Fluid Nozzle, 704/765 or 64 Air Nozzle
Airless Spray:	Graco - 30:1 pump, Contractor gun, 0.019 - 0.023" RAC IV tip

Note: Other equipment equivalent to the above may be used.

## PRECAUTIONS

For industrial use only.  
See the Altex Coatings Limited General Safety Data Sheet, product label and Material Safety Data Sheet (MSDS) for health and safety information prior to use.

**Altra-Prime<sup>®</sup> 514 Primer** is flammable. Keep away from heat, sparks and open flame. Use with adequate ventilation. May cause eye and skin irritation. Do not breathe vapour or spray. Wear suitable protective clothing such as gloves and eye and face protection.

## ALTEX COATINGS LIMITED

<b>Head Office New Zealand</b>  91-111 Oropi Road Greerton, Tauranga PO Box 142 Tauranga Mail Centre  Phone: +64 7 5411 221 Fax: +64 7 5411 310 www.altexcoatings.co.nz	<b>Head Office Australia</b>  7 Production Avenue Ernest Junction Queensland 4214 Australia  Phone: +61 7 5594-9522 Fax: +61 7 5594-9093 www.altexcoatings.com.au	<h3 style="margin: 0;">DISCLAIMER</h3> <p style="font-size: small; margin: 5px 0;">This is not a specification and all of the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.</p>
--	--	--